



**UTEX INDUSTRIES, INC.**  
*Taking Sealing Technology Beyond Tomorrow*  
 ISO 9001 Certified  
 www.utexind.com

# PRODUCT BULLETIN

UPB - 75      04/11/00  
 Rev. G      11/13/07

## CHEMTEX® I HIGH PERFORMANCE PERFLUOROELASTOMER (FFKM)

CHEMTEX® I is the latest in elastomer technologies from Utex Industries, Inc. The first generation of CHEMTEX elastomer is a proprietary alloy of perfluorinated elastomer polymers with a filler system to provide elastomer parts with exceptional chemical resistance, similar to PTFE, temperature capabilities from 20°F to 600°F, -7°C to 315°C with very low compression set.

CHEMTEX I is currently available in general purpose black compounds, a nominal 70, 80 and 90 durometer compound 7807, 7808 and 7809 as well as other specialty compounds suited for 600°F 70 and 90 duro, non-black 70 and 90 durometer and Rapid Gas Decompression (RGD) 70 and 90 duro.

CHEMTEX I is available in standard AN series o-rings and in custom molded articles and specialty shapes.

Below are the typical properties of CHEMTEX I standard compounds and a general comparison of chemical compatibility. UTEX Engineering Document ETS-018 provides a comparison of HTCR™ and CHEMTEX I over a much broader range of chemicals.

### TYPICAL PROPERTIES OF CHEMTEX® I COMPOUNDS

Compound No.	7807	7808	7809	78175	7819	7827	7828	7829	78975	7899
Specification									AMS-7257D	
Hardness (A) Nominal	70±5	80±5	90±5	75±5	95±5	75±5	80±5	90±5	75±5	90±5
S.G.	2.05	2.00	1.95	2.07	1.95	2.05	2.03	2.00	2.07	2.00
Hardness (A) Typical	73	80	91	75	95	75	80	90	75	92
Tensile Strength (psi)	2200	2150	2100	2400	2800	2100	2200	2500	2300	2300
E/B (%)	160	130	80	150	45	160	150	80	175	75
Modulus 50% (psi)	375	550	1550	400	-----	350	400	1350	500	2000
Modulus 100% (psi)	950	1350	-----	1050	-----	950	1200	-----	1300	-----
Tear "C" (pli)	100	125	150	150	220	150	150	160	100	125
Max Temperature °F	550	550	550	550	550	550	550	550	600	600
Typical Use*	GP	GP	GP	ED	ED	NB	NB	NB	HT	HT
Compression Set ASTM 395 B										
22 Hours @ 392°F with button	5	5	10	5	15	5	5	10	10	25
70 Hours @ 392°F with button	10	10	15	10	25	10	10	15	15	35
22 Hours @ 392°F with .250 CS o-ring	10	15	20	20	25	15	15	20	15	35
70 Hours @ 392°F with .250 CS o-ring	15	20	30	25	35	20	20	25	20	40

\*GP=General Purpose ED=Explosive Decompression Resistant NB=Non-Black HT=High Temperature

### GENERAL CHEMICAL RESISTANCE COMPARISON OF HTCR, FKM and CHEMTEX I

	HTCR	FKM	CHEMTEX I
High Temperature Steam/Hot Water	+	-	++
Caustics/High pH Fluids	+	-	++
Inorganic Acids	+	-	++
Phosphate Ester Hydraulic Fluid	+	+	++
Alcohols	+	-	++
Hydrocarbon Based Hydraulic Fluid	+	+	++
Water Glycol Hydraulic Fluid	+	-	++
Glycol Based Brake Fluids	+	+	++
Mineral or Silicon Oil Brake Fluids	+	-	++
Engine Oils (New Types)	+	-	++
Automatic Transmission Fluid (New Types)	+	-	++
Engine Coolants with Rust Inhibitors	+	-	++
Power Steering Fluid (New Types)	+	-	++
Sour (H2S) Oil and Gas	+	-	++
Amine Corrosion Inhibitors	+	-	++
Gasoline	-	+	++
EP Gear Lubricants	+	-	++
Gamma Ray Radiation	++	-	+
Polar Solvents	-	-	++
Non-Polar Solvents	+	-	++
Oxidizing Agents	-	-	++
High Aromatics (i.e., Toluene, Xylene)	-	+	++
Jet Turbine Oils	+	-	++
Pulp and Paper Liquors	+	-	++

“++” IS BEST “+” IS BETTER PERFORMANCE THAN “-”

**COMPARISON OF O-RING COMPRESSION SETS (.139 c/s)**

	<b><u>Kalrez®</u></b> <i>DuPont 1050LF</i>	<b><u>Chemraz®</u></b> <i>Greene Tweed CPD 505</i>	<b><u>ChemTex® I</u></b> <i>Utex 7807</i>
<b>22 Hours @ 392°F</b>	28.57	8.33	9.09
<b>70 Hours @ 392°F</b>	35.29	16.67	15.15
<b>22 Hours @ 450°F</b>	43.33	19.35	22.86
<b>70 Hours @ 450°F</b>	73.33	37.71	45.45

Kalrez® is a registered trademark of E.I. DuPont Co.  
 Chemraz® is a registered trademark of Greene Tweed Co.  
 ChemTex® is a registered trademark of Utex Industries, Inc.  
 HTCR™ is a trademark of Utex Industries, Inc

This information is believed to be reliable and correct, but our products discussed or described herein are sold without warranty, express or implied, as to the results the user may obtain with them, or as to the absence, existence or validity of patent rights of others that may be infringed by the use of this product. Statements herein concerning possible uses for our products should not be taken as inducements or recommendations to use these products to violate any particular patent.